



TECHNICAL BULLETIN

Haltech Inc.



465 CORONATION DRIVE
SCARBOROUGH, ONTARIO M1E 2K2
TELEPHONE: (416) 284-6111
FAX: (416) 284-6932

SUPERSET 1071

BASE:	HOMO POLYMER EMULSION
TOTAL SOLIDS %	50.5 - 53.5
VISCOSITY CPS @ 24°C:	7000 - 9000
RELATIVE DENSITY:	1.10 -1.12
pH VALUE:	4.3 – 4.5
COLOUR OF DRIED FILM:	CLEAR
CLEANER:	WATER (WET), MEK (DRY)
APPLICATION METHOD:	SPREADER, BRUSH, ROLLER COAT, ETC
SHELF LIFE:	3 MONTHS

GENERAL:

SUPERSET 1071 IS A FORMALDEHYDE FREE WOOD ADHESIVE.

SUPERSET 1071 IS A FAST DRYING ASSEMBLY WOOD GLUE FOR HARDWOODS, E.G. HICKORY, OAK. GOOD HEAT RESISTANCE. DEPENDING ON THE TYPE OF WOOD AND THE CONDITIONS UNDER WHICH THE GLUE IS USED, THE OPEN ASSEMBLY TIME IS APPROXIMATELY 2½ MINUTES.

PRESSING TIME IS ABOUT 1½ HOURS, BUT LIGHT HANDLING IS POSSIBLE AFTER 10 MINUTES.

WARRANTIES:

There is NO WARRANTY or condition, OF ANY KIND, written or oral, express or implied (INCLUDING NO WARRANTY OR MERCHANTABILITY OR FITNESS OF THE GOODS FOR THE PURPOSE CONTEMPLATED BY BUYER) concerning the goods sold hereunder or containers in which shipped and none shall be implied by law, EXCEPT THAT THE GOODS SHALL BE IN ACCORDANCE WITH SELLER'S SPECIFICATIONS.